

## **Rasaplast Non-Cementitious Base Coat**

### **Description**

- Decoplast Rasaplast Base Coat is a ready mixed 100% acrylic non-cementitious embedding base coat.
- It is applied with a standard stainless steel trowel.

### **Preparation**

- Decoplast Rasaplast Base Coat has been designed to be an embedding coat for applying Decoplast mesh to approved EPS foam.
- Surface and air temperature should be maintained at 45°F minimum during and at least 24 hours after the installation.

### **Mixing**

- Using a Goldblatt Jiffy Mixer, or equivalent, blend the Rasaplast to a uniform consistency. Remember: **DO NOT ADD WATER.**

### **Application**

#### **Base / Embedding Coat**

- The embedding base coat is stainless steel trowel applied. The base coat is spread to a uniform thickness of 1/8".
- Working in 40" strips, immediately embed with the trowel Decoplast mesh into the wet base coat, achieving a thickness just thicker than the embedded mesh. (No mesh should be visible.)
- Double wrap corners and overlap not less than 3" at mesh joints.
- Continue until the entire field is complete.

## Cleaning

- Clean equipment and containers with water immediately after use.

## Cautions

- Protect the material from freezing.
- Finishes must be applied at or above 45°F.
- Do not apply on damp surfaces or when rain is forecasted.
- Avoid inhaling dust.
- Handle with care.
- Consult the manufacturer's Material Safety Data Sheets.

## Coverage

- Each 65 pound pail has an approximate coverage of 100 square feet.

## Drying Time

- It is recommended to allow the basecoat application approximately 24 hours to dry. This estimate is based on optimum weather conditions of 70°F, with 55% relative humidity.
- Drying times will vary based on temperature and humidity.

## Availability

- Rasaplast Non-Cementitious Base Coat is available only at authorized Decoplast distributors.

## Warranty

- Consult your nearest Decoplast professional for details.

### Disclaimer

Decoplast, Inc. will not be held liable for incidental and consequential damages, directly or indirectly sustained, nor for any loss caused by application of these goods not in accordance with current manufacturers instructions or other than the intended use. Our liability is expressly limited to replacement of defective goods only. Any claim will be considered waived unless made in writing to us within thirty days from the date it was discovered.

**Decoplast, Inc.®**

(516) 354-4397 • [www.decoplast.com](http://www.decoplast.com)

352 Franklin Ave, Franklin Square, New York, 11010