

## **Decoplast Recover Coat**

### **Description**

- The Decoplast Recover Coat is a water based, sanded coating. This high performance coating can be brush or roller in an infinite variety of standard and custom colors.
- Recover Coat can be used over acrylic based finishes as well as stucco, masonry and concrete. Recover Coat is primarily use to change the color or refresh existing Decoplast finishes.

### **Preparation**

- The entire approved substrate must be clean and free of any contaminates.
- The surface and air temperature should be at a minimum of 45°F during and for at least 24 hours after the application.

### **Mixing**

- Using a Goldblatt Jiffy mixer, or equivalent, mix the coating until a uniform consistency is attained.

### **Application**

- Decoplast Recover Coat may be applied by roller or brush. By brush or 3/4" to 5/8" nap roller apply Recover Coat in multiple directions eliminating lap marks. First coat must completely dry before applying second coat.

### **Coverage**

- Coverage's will vary based on the amount of texture of the substrate. First coats will range between 350 – 500 square feet per pail. Second coats will range between 400 – 600 square feet per pail. Coverage's will be higher on smooth surfaces. It is recommended to a apply a minimum of two coats on any installation.

**Physical Properties**

Water Vapor Permeability – ASTM E96..... Permeable

Mildew Resistance – Mil Std 810B..... Passes

Freeze / Thaw .....passes 7 cycles

**Cleaning**

- Clean equipment and containers with water immediately after use.

**Cautions**

- Protect the material from freezing.
- Finishes must be applied at or above 45°F.
- Do not apply on damp surfaces or when rain is forecasted.
- Consult the manufacturer’s Material Safety Data Sheets.

**Availability**

- Decoplast Top Coat Finish is available only at authorized Decoplast distributors.

**Warranty**

- Consult your nearest Decoplast professional for details.

**Disclaimer**

Decoplast, Inc. will not be held liable for incidental and consequential damages, directly or indirectly sustained, nor for any loss caused by application of these goods not in accordance with current manufacturers instructions or other than the intended use. Our liability is expressly limited to replacement of defective goods only. Any claim will be considered waived unless made in writing to us within thirty days from the date it was discovered.